

Honeywell ACumist® Micronized Polyolefin Waxes

Typical Properties

Product	Microns Average (mv)	Microns Maximum (<99.9%)	Mettler Drop Point (ASTM D-3954)	Density, g/cc (AST-MD-1505)	Hardness, dmm (ASTM D-5)	Acid Number, mg KOH/g (ASTM D-1386)	Performance Advantages
---------	----------------------	--------------------------	----------------------------------	-----------------------------	--------------------------	-------------------------------------	------------------------

High Density Oxidized Polyethylene Homopolymers

ACumist A-6	6.0-7.5	22	137 °C 279 °F	0.99	<0.5	26-40	<ul style="list-style-type: none"> • Surface functionality for water wettability and to promote adhesion to topcoats • Outstanding slip, abrasion resistance and toughness • Controlled maximum particle size for a consistent grind • For solvent, water and UV based systems • Excellent matting without burnishing
ACumist A-12	10.0-13.0	44					
ACumist A-18	16.0-19.0	65					
ACumist A-1812 ¹	8.3-9.3	26	139 °C 282 °F	0.99	<0.5	16-19	<ul style="list-style-type: none"> • Special FDA 175.300 compliant oxidized HDPE wax • All comments above for "A" series also apply

Polyethylene Homopolymers

ACumist B-6	6.0-7.5	22	126 °C 259 °F	0.96	<1.0	Nil	<ul style="list-style-type: none"> • Insoluble in solvent and UV based systems at RT • Excellent abrasion resistance with good slip • FDA 175.300 and other compliances • Controlled maximum particle size for a consistent grind • Minimal gloss reduction
ACumist B-9	8-10	44					
ACumist B-12	10.0-11.5	44					
ACumist B-18	14.0-17.0	62	121 °C 250 °F	0.95	<1.0	Nil	<ul style="list-style-type: none"> • Insoluble in solvent and UV based systems at RT • Excellent slip with good abrasion resistance • FDA 175.300 and other compliances • Controlled maximum particle size for a consistent grind • Good gloss retention for the smaller size grades
ACumist C-5	4.5-5.5	16					
ACumist C-12	10.0-13.0	44					
ACumist C-18	14.0-17.0	62	118 °C 244 °F	0.94	<2.0	Nil	<ul style="list-style-type: none"> • A good balance of properties and economy
ACumist D-9	8.0-10.0	31					
ACumist D-12	10.0-13.0	44					

Polypropylene Homopolymer

ACumist P-5 ¹	5.0-6.0	16	145 °C 293 °F	0.91	<0.5	Nil	<ul style="list-style-type: none"> • High coefficient of friction for "non-skid" performance • Excellent abrasion resistance • Good matting performance • Controlled maximum particle size for a consistent grind
ACumist P-10 ¹	8.0-10.0	31					

PPTFE Modified Polyethylene

ACumist 3105B ¹	6.0-7.5	22	126 °C 259 °F	0.98	<0.5	Nil	<ul style="list-style-type: none"> • Enhanced slip and abrasion performance • Lowest particle size for thin film, high performance applications
ACumist 3405 ¹	4.5-5.5	16	121 °C 250 °F	1.10			

¹ Minimum order quantities and extended order lead times may apply.

For additional information or to contact us, please visit:
honeywell-additives.com



2256 PA v2 | January 2018
©2018 Honeywell International Inc. All rights reserved.

All statements, information and data given herein are believed to be accurate and reliable, but are presented without guarantee, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that measures may not be required.